



ALIGNMENT METHOD, ALIGNMENT SUBSTRATE, PRODUCTION METHOD
OF ALIGNMENT SUBSTRATE, EXPOSURE METHOD, EXPOSURE
APPARATUS AND PRODUCTION METHOD OF MASK

5

TECHNICAL FIELD

The present invention relates to an alignment method, an alignment substrate, a production method of an alignment substrate, an exposure method, an exposure apparatus and a production method of a mask.

10

BACKGROUND ART

Conventionally, in a production process of a semiconductor device, a lithography technique using an ultraviolet ray has been mainly used in a step of transferring a circuit pattern, such as wiring, to a semiconductor substrate. In recent years, semiconductor devices have been developed to be highly integrated and, along therewith, there are more demands for furthermore miniaturizing wiring and other circuit patterns than before. However, as the miniaturization proceeds, pursuit of a shorter wavelength of a lithography light source has been on the way to deadlock and a new exposure technique has been expected.

A lithography technique using a charged particle beam typified by an electron beam and X-ray has gathered attentions. In the charged particle beam or X-ray

lithography, a membrane mask or a stencil mask, wherein a wafer is the base, is used.

FIG. 1A is a sectional view of a membrane mask. The membrane mask 101 is obtained by arranging on an
5 extremely thin membrane 102 for transmitting a charged particle beam or an X-ray an absorbing material 103 for reflecting/scattering/absorbing the charged particle beam or X-ray corresponding to a circuit pattern shape to be exposed. On a surface on the side not formed with the
10 absorbing material 103 of the membrane 102 are formed beams 104 and supporting frame portions 105 by performing etching, for example, on a silicon wafer.

FIG. 1B is a sectional view of a stencil mask. The stencil mask 106 is obtained by providing opening
15 portions 108 corresponding to a circuit pattern shape to be exposed on a thin membrane 107 for reflecting/scattering/absorbing the charged particle beam or X-ray. On a surface on one side of the membrane 107 are formed beams 104 and supporting frame portions 105 by
20 performing etching, for example, on a silicon wafer. In the etching for forming the beams 104 and the supporting frame portions 105, the membrane 107 is protected from being etched by an etching stopper layer 109 ~~from being etched~~. As explained above, either of the masks uses a
25 thin film (membrane).

On the other hand, a high positional accuracy ~~is~~

also is required to a mask, as the circuit pattern becomes miniaturized. Generally, electron beam lithography is used for mask exposure for forming a pattern on a mask, and accurate alignment of an electron beam for performing exposure is required for attaining high positional accuracy.

However, even if a beam is sufficiently aligned at the time of starting mask exposure, since an electron beam exhibits a phenomenon called drift when drawing a pattern, inaccuracy increases in a certain direction over time. Accordingly, to maintain sufficient accuracy, drawing of a pattern is suspended cyclically in accordance with a the drift amount of the electron beam, and when an alignment error exceeds tolerance, the beam position is adjusted again.

The beam position adjustment is performed by irradiating an electron beam to, for example, a mark made by tungsten on a stage and detecting reflected electrons, and it is based on the detection result of a stage position at that time. In the electron beam position adjustment, the stage is moved from a stage position for performing exposure to a stage position for detecting, so that an error may be actually introduced due to a slip of the stage or a stress relating to other movement. Furthermore, due to the moving of the stage, an excessive time is required other than performing exposure, which

results in a decline of throughput.

To perform the alignment of the electron beam with high accuracy, there has been proposed a system called Spatial-phase-locked electron beam lithography (SPLEBL) by the MIT in the United States (refer to the specification of the U.S. Patent No. 5892230 and an article "Spatial-phase-locked Electron-beam Lithography: Initial Test Results" pp 2342 to 2345, J. Vac. Sci. Technol. B. Vol. 11, No. 6 Nov. Dec. 1993).

Also, another alignment technique has been proposed by the Naval Research Laboratories (NRL) (refer to the specification of the U.S. Patent No. 5703373 and the article "Improving pattern placement using through-the-membrane signal monitoring", J. Vac. Sci. Technol. B 16(6), Nov/Dec 1998, pp 3567 to 3571). In this technique, an alignment grid is placed immediately under an X-ray membrane, and the alignment grid forms a Schottky diode junction. Since the Schottky diode junction functions as a detector of an incident electrons, alignment information can be obtained by an electron beam for performing exposure in the same way as in the method by the MIT.

Also, a method of providing two kinds of alignment marks on a mask (reticle) and correcting the distortion of the reticle at the time of mask exposure has been disclosed (refer to the Japanese Unexamined Patent

Publication No. 2000-124114). In this method, the entire pattern is divided to small regions (sub-fields), a charged particle beam is irradiated to every sub-field, and sub-field images are combined on a substrate to transfer and ~~exposure~~ expose the entire pattern, ~~—, —~~ wherein first alignment marks are arranged between the sub-fields and the second alignment marks are arranged on the sub-fields. By using two kinds of alignment marks, a distortion ~~arisen~~ arising at the time of loading the reticle to an exposure apparatus and a distortion due to errors, etc. at the time of producing the reticle are detected and corrected.

Furthermore, there has been disclosed a method of fixing a position detection member produced separately from the mask to an X-ray mask instead of forming position reference marks on the mask by etching and using the same for position detection at the time of drawing a mask pattern (refer to the Japanese Unexamined Patent Publication No. 2000-31008).

Among the above conventional arts, in the SPLEBL, special alignment marks are provided on a substrate, ~~allover~~ the substrate surface is scanned all over by an electron beam for exposure, and a returned signal is detected to obtain alignment information at the same time as the exposure. Therefore, a high positional accuracy can be obtained, ~~—, —~~ however, as a first problem, the

special alignment marks have to be provided on the substrate in advance.

Also, the alignment marks are arranged on a pattern and a non-pattern at several μm pitches. Since drawing is performed while reading a signal of alignment information at all alignment marks, as a second problem, exposure becomes slow.

As a third problem, since exposure on the overall resist surface on the substrate is performed by an electron beam for reading a signal of alignment information, latent image contrast declines. Due to these problems, the SPLEBL is used only on an experimental level.

In the NRL method, being different from the SPLEBL, alignment marks are made not on the substrate but are made below the membrane, so that the first problem of the SPLEBL is solved. However, the second and third problems still remain.

Also, in the case of the method described in the Japanese Unexamined Patent Publication No. 2000-124114, the first and second alignment marks are formed on the reticle, so that there is the same problem as the first problem of the SPLEBL.

The method described in the Japanese Unexamined Patent Publication No. 2000-31008 is effective for preventing contamination on the mask due to dusts

generated in an etching step for forming the position reference marks and the subsequent washing step, but the position reference marks cannot be provided on the membrane, so that a plurality of position reference marks
5 cannot be arranged evenly on the mask.

DISCLOSURE OF THE INVENTION

The present invention was made in consideration of the above problems, and therefore, an object of the
10 present invention is to provide an alignment method capable of aligning with high accuracy without providing alignment marks on a mask and preventing a decline of throughput of exposure and a decline of latent image contrast due to alignment, an alignment substrate, a
15 production method of an alignment substrate, an exposure method, an exposure apparatus and a production method of a mask.

To attain the above object, an alignment method of the present invention is characterized by comprising: a
20 step of transmitting an exposure beam from a first surface side of a thin film to a second surface side and reflecting said exposure beam on a plurality of alignment marks arranged on said second surface side of said thin film and outside said thin film; a step of detecting said
25 exposure beam reflected on said alignment marks at said first surface side and detecting positions of said

alignment marks; and a step of obtaining position coordinates on said thin film using said detected position of said alignment marks.

Also, to attain the above object, an alignment
5 substrate of the present invention is characterized by being arranged so that a surface thereof faces a second surface of a thin film at said second surface side of said thin film, into a first surface thereof an exposure
beam ~~entering~~enters, and comprising a plurality of
10 alignment marks formed on said surface and reflecting said exposure beam transmitting and entering through said thin film at a higher reflectance than said surface at a periphery thereof.

To attain the above object, a production method of
15 an alignment substrate of the present invention is characterized by comprising: a step of forming an etching stopper layer on a first substrate; a step of forming a
second substrate on said etching stopper layer; a step of
forming a plurality of alignment marks on a part of said
20 second substrate; a step of performing an etching to a surface layer portion of said second substrate using said alignment marks as a mask, and forming a step between a surface of said second substrate directly below said alignment marks and a surface of said second substrate at
25 a periphery of said alignment marks; a step of forming a resist on said alignment marks and on a part of said

second substrate at a periphery of said alignment marks;
a step of performing an etching to said second substrate
using said resist as a mask until said etching stopper
layer is exposed; and a step of removing said resist.

5 To attain the above object, an exposure method of
the present invention is characterized by comprising: a
step of measuring ~~a~~-position coordinates of ~~a~~-alignment
marks in an alignment substrate having a plurality of
said alignment marks thereon; a step of arranging said
10 alignment substrate so that a surface thereof faces a
second surface of a thin film at said second surface side
of said thin film, on a first surface thereof a resist
being made,—; a step of transmitting an exposure beam
from said first surface side of said thin film to said
15 second surface side and reflecting said exposure beam on
said alignment marks; a step of detecting said exposure
beam reflected on said alignment marks at said first
surface side and detecting positions of said alignment
marks; a step of determining positions for drawing a mask
20 pattern on said resist using said detected positions of
said alignment marks; and a step of drawing said mask
pattern on said resist by an exposure of a charged
particle beam, an extremely-short ultraviolet ray, an X-
ray, an ultraviolet ray, and/or a radiation.

25 To attain the above object, an exposure apparatus
of the present invention is characterized by comprising:

a thin film holding means for holding a thin film applied
with a resist on a first surface thereof; an alignment
substrate holding means for holding an alignment
substrate having a plurality of alignment marks on a
5 surface thereof at a second surface side of said thin
film so that said second surface of said thin film faces
said surface; an alignment detecting system irradiating
an exposure beam at said first surface, reflecting said
exposure beam on said alignment marks via said resist and
10 said thin film, detecting said exposure beam reflected on
said alignment marks at said first surface side, and
measuring position coordinates of said alignment marks;
and a charged particle beam source, an extremely-short
ultraviolet ray source, an X-ray source, an ultraviolet
15 ray source, and/or a radiation source for drawing a mask
pattern on said resist.

To attain the above object, a production method of
a mask of the present invention is characterized by
comprising: a step of applying a resist on a first
20 surface of a thin film; a step of arranging an alignment
substrate having a plurality of alignment marks on a
surface thereof at a second surface side of said thin
film so that said second surface of said thin film faces
said surface; a step of transmitting an exposure beam
25 from said first surface side of said thin film to said
second surface side and reflecting said exposure beam on

said alignment marks; a step of detecting said exposure
beam reflected on said alignment marks at said first
surface side and detecting positions of said alignment
marks; a step of determining positions for drawing a mask
5 pattern on said resist using said detected positions of
said alignment marks; a step of drawing said mask pattern
on said resist by an exposure of a charged particle beam,
an extremely-short ultraviolet ray, an X-ray, an
ultraviolet ray, and/or a radiation; a step of developing
10 said resist; a step of performing an etching to said thin
film using said resist as a mask and forming openings
along said mask pattern; and a step of removing said
resist.

Due to the above, alignment of a thin film can be
15 performed with high accuracy without providing alignment
marks on the thin film. An alignment substrate may be
used for alignment of other thin film, on which a
different mask pattern is drawn. Also, it ~~becomes~~ also
20 becomes possible to perform alignment by using a charged
particle beam, an extremely-short ultraviolet ray, an X-
ray and/or a radiation to be used for performing exposure
of a mask pattern.

BRIEF DESCRIPTION OF DRAWINGS

25 FIG. 1A is a sectional view of a membrane mask, and
FIG. 1B is a sectional view of a stencil mask.

FIG. 2A is a sectional view of a-mask blanks to be aligned by the alignment method of the present invention, FIG. 2B is a sectional view of an alignment substrate of the present invention, and FIG. 2C is a sectional view showing a state where the mask blanks in FIG. 2A and the alignment substrate in FIG. 2B are set.

FIG. 3 is an example of a view from above of the mask blanks shown in FIG. 2A.

FIG. 4 is another example of a view from above of the mask blanks shown in FIG. 2A.

FIG. 5A to FIG. 5C are sectional views showing production steps of a production method of an alignment substrate of the present invention.

FIG. 6A to FIG. 6C are sectional views showing production steps of a production method of an alignment substrate of the present invention, continued from FIG. 5C.

FIG. 7A to FIG. 7C are sectional views showing production steps of a production method of an alignment substrate of the present invention, continued from FIG. 6C.

FIG. 8 is a sectional view showing an alignment method of the present invention.

FIG. 9A and FIG. 9B are examples of a-sectional views of a-mask blanks to be aligned by the alignment method of the present invention.

FIG. 10A is another example of a sectional view of
a-mask blanks to be aligned by the alignment method of
the present invention, and FIG. 10B is a sectional view
showing a state where the mask blanks in FIG. 10A and the
5 alignment substrate of the present invention are set.

FIG. 11 is a sectional view showing another example
of the alignment method of the present invention.

BEST MODE FOR CARRYING OUT THE INVENTION

10 Below, preferred embodiments of an alignment method,
an alignment substrate, a production method of an
alignment substrate, an exposure method, an exposure
apparatus and a production method of a mask of the
present invention will be explained with reference to the
15 drawings. In the present embodiments, lithography for
forming a mask pattern on a stencil mask will be
explained.

FIG. 2A is a sectional view showing a-mask blanks 1
before exposing a mask pattern, and FIG. 2B is a
20 sectional view of an alignment substrate 11 of the
present embodiment. FIG. 2C is a sectional view showing a
state where the mask blanks 1 in FIG. 2A and the
alignment substrate 11 in FIG. 2B are set.

As shown in FIG. 2A, the membrane 2 is applied with
25 a photosensitive resist 3 to an electron beam. While a
material of the membrane 2 is not limited, it is single

crystal silicon membrane in the present embodiment. A surface on a side not applied with the resist 3 of the membrane 2 is formed with beams 4 and supporting frame portions 5 by performing etching on a silicon wafer.

5 FIG. 3 is an example of a plan view of the mask blanks 1 in FIG. 2A, and the beams 4 are arranged, for example, in a lattice shape, as shown in FIG. 3. By forming the beams 4, flexure of the membrane 2 is prevented. Opening portions are formed to be a desired
10 circuit pattern shape on portions not formed with the beams 4 and the supporting frames 5. Formation of the opening portions is performed by using as a mask a resist pattern obtained by performing exposure and development on the resist 3 in FIG. 2A.

15 FIG. 4 is another example of a plan view of the mask blanks 1 in FIG. 2A. As shown in FIG. 3, a circuit pattern (opening portions) cannot be arranged on the beam 4 portions on a stencil mask formed with the beams 4. Accordingly, a circuit pattern superimposing with the
20 beam 4 portions has to be arranged on a different stencil mask (complementary mask) wherein the position of the beams 4 is different.

On the other hand, in the mask blanks 1 shown in FIG. 4, a region inside the supporting frame 5 is divided
25 into four regions by ~~mutually perpendicular~~ two straight mutually perpendicular lines "a" and "b", and beams 4 are

formed so as to be shifted from one another on the four regions. A circuit pattern to be formed on the four regions is transferred by exposure by being superimposed on the same position on the wafer.

5 When the beams 4 are arranged as shown in FIG. 4, a circuit pattern on portions formed with the beams 4 on a certain region can be arranged on ~~either~~ another region on the mask, so that it is not necessary to produce and use a plurality of complementary masks. The mask blanks 1
10 shown in FIG. 3 and FIG. 4 differ only on the arrangements of the beams 4, and the sectional configuration and the production method are the same.

 In FIG. 3 and FIG. 4, a the size of a portion surrounded by the beams 4 may be set in a range capable
15 of preventing flexture of the membrane 2 and may be suitably changed in accordance with a material and a thickness of the membrane 2. As an example, when the beams 4 are arranged in a lattice shape on one surface of the silicon membrane 2, a length of a side of a square
20 surrounded by the beams 4 can be made to be 1 mm or so and a width of the beams 4 can be made to be 100 to 200 μ m or so.

 In the sectional configuration of the mask blanks 1 shown in FIG. 2A, an etching stopper layer 6, for example,
25 made by a silicon oxide film is formed between the layers of the membrane 2 and the beams 4 or membrane 2 and the

supporting frame portions 5. The etching stopper layer 6 protects the membrane 2 from being etched in a step of performing etching on the silicon wafer to form the beams 4 and the supporting frame 5.

5 The mask blanks configured as above can be produced, for example, by using a SOI (silicon on insulator or semiconductor on insulator) substrate. In this case, the beams 4 and the supporting frame portions 5 are formed of the SOI silicon wafer, a buried oxidized film of the SOI
10 substrate is used as an etching stopper layer 6, and the silicon layer is used as the membrane 2.

As shown in FIG. 2B, the alignment substrate 11 has alignment marks 12 on the outermost surface. Alignment mark supporting portions 13 are formed on the substrate
15 14 via an etching stopper layer 15. The alignment mark supporting portions 13, as a lower layer of the alignment marks 12, have a shape ~~that~~ around the alignment marks 12 that is ditched. The surface of the portion, where the alignment mark supporting portion 13 is formed by
20 ditching, around the alignment mark 12 will be referred to as a step portion 13a.

When performing exposure on the resist 3 on the surface of the mask blanks 1 in FIG. 2A, as shown in FIG. 2C, the beams 4 and the supporting frame portions 5 of
25 the mask blanks 1 are set between the alignment mark supporting portions 13 of the alignment substrate 11, and

lower ends of the beams 4 and the supporting frame portions 5 are placed on the etching stopper layer 15.

A height "a" shown in FIG. 2B indicates a height of the alignment mark supporting portion 13 and the alignment mark 12 together. The height "a" is set in accordance with the structure of the mask blanks 1 in FIG. 2A. In the mask blanks 1, when the beams 4 and the supporting frame portions 5 are formed by performing etching on a silicon wafer having a diameter of 8 inches (200 mm), since a thickness of the 8-inch wafer is 725 μm , a distance "b" (refer to FIG. 2C) from the beams 4 or the supporting frame portions 5 to the membrane 2 becomes a sum of 725 μm and a thickness of the etching stopper layer 6. The height "a" is made less than the distance "b", but it is preferable to be that it is as close to the distance "b" as possible.

While a thickness of the membrane 2 differs in accordance with a the material of the membrane 2 and the energy of a charged particle beam to be used for exposure, it is generally extremely thin, as 0.1 μm to 2 μm or so, so that when the alignment marks 12 on the alignment substrate 11 contact the membrane 2, the membrane 2 is liable to be damaged. Accordingly, positional adjustment in the height direction of the mask blanks and the alignment substrate is significant.

On the other hand, while the production method will

be explained later on, the alignment mark supporting portions 13 on the alignment substrate 11 can be formed also by using a silicon wafer. For example, when forming the alignment mark supporting portions 13 by using an 8-
5 inch wafer, the height "a" becomes a sum of 725 μm and a thickness of the alignment marks 12.

A distance "c" from tips of the alignment mark 12 to the step portions of the alignment mark supporting portions 13 depends on ~~an~~the accelerating voltage of ~~an~~
10 the electron beam exposure apparatus (mask exposure apparatus) to be used for mask exposure. At the time of mask exposure, when electrons transmitted through the membrane 2 reflect on the step portions 13a and enters again to the resist 3 on the membrane 2, resolution of
15 the exposure pattern declines. To prevent this, it is preferable that the distance "c" is about 10 μm or more, for example, when the accelerating voltage is 50 to 100 kV.

Due to the configuration ~~that~~in which the
20 alignment mark supporting portions 13 are ditched on portions other than the alignment marks 12, the reflection strength against an electron beam can be remarkably lowered on the alignment mark supporting portions 13 as comparing compared with that on alignment
25 marks 12, for example, made by tungsten, etc. Namely, it becomes possible to detect the alignment marks 12 at a

high contrast, and the S/N ratio of a mark signal is improved.

Also, ~~a~~the material of the alignment mark supporting portions 13 is preferably a substance having a small atomic weight so as to suppress the reflection of an excessive electron beam. In the present embodiment, in terms of ease of processing and prevention of contamination of the mask blanks 1, the alignment mark supporting portions 13 are formed by performing etching on a silicon wafer.

Positions and density of forming the alignment marks 12 are not particularly limited, but in the case where the portion surrounded by the beams 4 is about 1 mm-square, as an example (refer to FIG. 3 and FIG. 4), it is preferable that at least one, preferably ~~a~~several, alignment marks 12 are arranged on one alignment mark supporting portion 13 so as to be set on a portion surrounded by the beams 4.

Even in the case of arranging several alignment marks 12 on one alignment mark supporting portion 13, intervals of the alignment marks 12 become several hundreds of μm , that is, the mark intervals are obviously wider as comparing compared with the case of the SPLEBL explained above. Accordingly, even though drawing is performed while reading a signal of position information at the alignment marks, the exposure speed does not

notably lowered as in the SPLEBL.

Also, according to the present embodiment, the alignment marks 12 are arranged not on the membrane 2 of the mask blanks 1 but on the alignment substrate 11, so
5 that the alignment marks 12 can be formed either on a pattern or non-pattern under a later explained certain condition. However, the mark density is lower as
comparing compared with that in the SPLEBL, so that the alignment marks 12 can be arranged selectively on a non-
10 pattern. Accordingly, it is possible to prevent the deterioration of latent image contrast due to reading of position information on all over the resist surface, which is observed in the SPLEBL for arranging marks at high density on a pattern and a non-pattern.

15 A thickness of the alignment marks 12 depends on an alignment light and a charged particle beam (electron beam) for alignment, etc. (hereinafter, these will be collectively called as an exposure beam for alignment), but 0.1 to 5 μm or so is preferable when a high
20 acceleration electron beam used for mask exposure is used for alignment. When the thickness of the alignment marks 12 is too thin, the reflection strength of an exposure beam for alignment becomes weak and alignment accuracy declines. When the thickness of the alignment marks is
25 too thick, etching of an alignment mark formation layer 22, which will be explained with reference to FIG. 5A

later on, becomes difficult.

Next, a production method of producing an alignment substrate of the present embodiment will be explained. In the production method of an alignment substrate of the present embodiment, processing on the alignment mark supporting portion 13 is performed by dividing to two stages. Due to this, the step portions 13a of the alignment mark supporting portions can be formed to be a desired height.

FIG. 5A is a sectional view showing a substrate for producing an alignment substrate 11 shown in FIG. 2. As shown in FIG. 5A, for example, a silicon oxide film is formed as an etching stopper layer 15 on a first silicon wafer as a substrate 14. A second silicon wafer 21 is formed on the silicon oxide film 15 and, for example, a tungsten layer is formed thereon as an alignment mark formation layer 22.

The substrate (first silicon wafer) 14 is assumed to have a thickness capable of supporting the entire substrate, so that the entire substrate shown in FIG. 5A does not bend. As the substrate 14, a standardized wafer used for producing a semiconductor device, etc. can be used and, specifically, the thickness is 525 μm in the case of a silicon wafer having a diameter of 4 inches, (200 mm) and 725 μm in the case of an 8-inch wafer.

Instead of using a silicon wafer as the substrate

14, a silica substrate, etc. may be used. Also, as a material of the alignment mark formation layer 22, for example, tantalum, platinum, gold, iridium and ~~ether-~~ metals ~~may be used~~ other than tungsten may be used. Also,
5 as the etching stopper layer 15, a silicon nitride film, etc. may be formed.

The etching stopper layer 15 preferably has a thickness so as not to disappear in a ~~later~~ later- explained etching step of the second silicon wafer 21,
10 that is, about 1 μ m or thicker. ~~A~~ The thickness of the second silicon wafer 21 is determined based on a height of beams and a supporting film portion of the stencil mask (refer to FIG. 2).

Next, as shown in FIG. 5B, a resist 23 is formed to
15 be a pattern of alignment marks 12 (refer to FIG. 2) on the alignment mark formation layer 22 ~~as shown in FIG. 5B~~. To form the resist 23 to be a pattern of alignment marks 12, after applying the resist to the whole surface, exposure is performed by an electron beam and an
20 ultraviolet ray, etc. for development. Next, as shown in FIG. 5C, etching is performed on the alignment marks formation layer 22 by using the resist 23 as a mask to form alignment marks 12 made by tungsten.

Next, as shown in FIG. 6A, the resist 23 and the
25 alignment mark 12 are used as masks to perform etching to a predetermined depth on a surface portion of the second

silicon wafer 21. A part of the surface obtained by the etching becomes a step portion 13a of the alignment mark supporting portion (refer to FIG. 2). After that, as shown in FIG. 6B, the resist 23 is removed and washing is performed.

Next, as shown in FIG. 6C, to process the remaining portion of the second silicon wafer 21, a resist 24 is applied to the whole surface. At this time, a positive--type resist is preferably used as the resist 24. In the present embodiment, there is a level difference between the alignment mark 12 part and the other part (ditched portions 13a of the alignment mark supporting portions), and a part of the resist on the ditched portion 13a as the lower level is removed.

Since an exposed part becomes soluble in a positive--type resist, it is sufficient to focus only on the lower level side when using the positive--type resist, and it is not necessary to have a focus depth by which both of the upper level (resist on the alignment marks 12) and the lower level are suitably exposed. Because the resist 24 is left on all of the upper level, the resist on the upper level does not have to be exposed when using a positive--type resist.

Next, as shown in FIG. 7A, exposure and development are performed on the resist 24, and only the resist 24 on a part for forming the alignment mark supporting portions

13 (refer to FIG. 2) is left.

Next, as shown in FIG. 7B, etching is performed on the second silicon wafer 21 by using the resist 24 as a mask until the etching stopper layer 15 exposes, and the
5 alignment mark supporting portions 13 are formed.

It is also possible to finish the etching at a stage ~~that~~ in which etching of an amount of a thickness of the second silicon wafer 21 is performed, for example, by controlling an etching amount by the etching time and
10 without using an etching stopper layer. But by using the etching stopper layer 15, the flatness degree on the etching surface can be improved.

Since the beams 4 and the supporting frame portions 5 of the mask blanks 1 (refer to FIG. 2) are placed on
15 the portions where the second silicon wafer 21 is removed, when the surface flatness degree is poor, the mask blanks cannot be stably set and positional accuracy at mask exposure declines. To prevent this, it is preferable to provide the etching stopper layer 15 as a base of the
20 second silicon wafer 21.

On the other hand, in a step of performing etching on the second silicon wafer 21 partway to form the step portions 13a (refer to FIG. 6A), it is sufficient if an
| etching depth ~~that~~ in which an exposure beam for
25 alignment reflected on the step portions 13a does not enter the resist for mask pattern transfer (resist of

mask blanks) is obtained. Accordingly, the surface flatness degree is not required as in performing etching of an amount of a thickness of the second silicon wafer 21, and etching can be performed without providing an etching stopper layer.

After that, as shown in FIG. 7C, by removing the resist 24 and washing, the alignment substrate 11 is completed.

The produced alignment substrate 11 is measured for positions of the alignment marks 12 with high accuracy before being used for mask exposure. Position coordinates of the measured alignment marks 12 are input to a mask exposure apparatus. At the time of mask exposure, the input position coordinates and alignment mark detection results of the mask exposure apparatus are matched, and mask exposure is performed so as not to cause distortion on a pattern to be transferred. When mask exposure is performed in a state where alignment is performed under a condition that position coordinates input to the mask exposure in advance matches with alignment mark detection results of the mask exposure, a pattern without distortion can be transferred.

Note that in the case where positional accuracy is insufficient when a position of a pattern exposed on the mask blanks 1 (refer to FIG. 2) is measured, or in the case where the pattern position is deviated when exposure

is performed on the wafer by using a stencil mask obtained by performing etching on the membrane after mask exposure, the above alignment may be corrected.

Next, a method of performing mask exposure by using
5 the alignment substrate of the present embodiment will be explained in detail. In the mask blanks 1 shown in FIG. 2, the mask blanks 1 does not have to be specially devised if the resist 3 on the mask blank is not exposed by the electron beam for alignment. Also, in this case, even if
10 a pattern is arranged on the membrane on the alignment marks 12, the resist 3 is not exposed in alignment, so that the alignment marks 12 can be arranged regardless of the pattern position.

As a specific example of the case where the resist
15 3 is not exposed by the exposure beam for alignment, the case of performing mask exposure by an electron beam having an acceleration voltage of 50 kV and using a laser beam having a wavelength of 780 nm as the exposure beam for alignment may be mentioned. FIG. 8 shows a sectional
20 view for performing alignment in such a case. As shown in FIG. 8, the exposure beam for alignment 16A transmits the membrane 2 and the resist 3 thereon and enters the alignment marks 12.

Alignment accuracy required at this time depends on
25 a margin of matching the membrane 2 with a mask pattern drawn on the resist 3. When the margin for matching the

membrane 2 and the mask pattern is small, mask side alignment marks, which can be detected by the exposure beam for alignment, are provided on the membrane 2 of the mask blanks 1 by following the conventionally--known
5 method.

FIG. 9A is an example of forming the mask side alignment marks 7 on a portion not formed with a pattern (opening portions in the case of a stencil mask) near the beams 4. As the mask side alignment marks 7, other than
10 using opening portions formed by performing etching for an amount of a thickness of the membrane 2 as shown in FIG. 9A, recessed portions formed by performing etching on the surface portion of the membrane 2 also may be--also used.

15 Also, as shown in FIG. 9B, mask side alignment marks 7 can be formed by removing a part of the membrane 2 on the beams 4 by etching. The mask side alignment marks 7 may be any as far as they have a different transmittance to the exposure beam for alignment from
20 that on the peripheral portion, and they do not interfere with the exposure beam for alignment to irradiate to the alignment marks on the alignment substrate--is not interfered.

On the other hand, in FIG. 8, positions of the
25 alignment marks 12 on the alignment substrate 11 are detected by the exposure beams for alignment transmitting

through the mask blanks 1. The exposure beam for alignment 17A reflected on the alignment marks 12 is detected by the light detector 18A.

When the mask side alignment marks are provided, alignment of the mask blanks 1 and the alignment substrate 11 is performed by using the measured positions of the mask side alignment marks and positions of the alignment marks 12. After that, mask exposure is performed by referring to position coordinates of the alignment marks 12 input to the mask exposure apparatus in advance. After the mask exposure, by developing a resist and performing etching on the membrane 2 by using the resist as a mask, a lithography mask is obtained.

When the margin for matching the membrane 2 and the mask pattern is large, even if the mask side alignment marks are not specially provided, alignment of the mask blanks 1 and the alignment substrate 11 can be performed based on positions of the beams 4 detected by the exposure beam for alignment transmitting through the membrane 2 and the positions of the alignment marks 12.

In the case where a resist on the mask blanks is exposed by the exposure beam for alignment, the resist 3 on the alignment marks 12 in FIG. 2C is removed by development after mask exposure. As a result, in a step of performing etching on the membrane 2 by using the resist 3 as a mask to form opening portions (opening

portions corresponding to the opening portions 108 in FIG. 1B), opening portions are formed also on portions irradiated with the exposure beam for alignment.

When the opening portions becomes problematic when
5 using the mask for exposing the wafer (in the lithography step in producing a semiconductor device), for example, a mask blanks having a protective film as below ~~is~~ are used as the countermeasure. FIG. 10A is a sectional view of a mask blanks having the protective film.

10 The mask blanks in FIG. 10A ~~has~~ have a protective film 8 at positions on the alignment marks 12 and not superimposing with a pattern on the membrane 2 when being combined with the alignment substrate 11, as shown in FIG. 10B. A Configuration ~~configuration~~ other than that is the
15 same as that in the mask blanks 1 in FIG. 2A.

In the present embodiment, single crystal silicon is used as a material of the membrane 2, so that, for example, a silicon-oxide film is formed as a protective film 8, and the membrane 2 is protected by the protective
20 film 8 even if the resist 3 is removed. To form the protective film 8, before applying the resist 3 to the membrane 2, a silicon-oxide film is formed all over the membrane 2, for example, by the ~~chemical~~ vapor deposition (CVD) and removed by etching so as to be left only on the
25 alignment marks.

As a material of the protective film 8, any

material other than silicon-oxide ~~silicon~~ may be used as
~~far~~ long as it is not etched in a step of performing
etching on the silicon membrane and it transmits the
exposure beam for alignment when made to be a thin film
5 having a thickness of the protective film 8. For example,
instead of forming the protective film 8 in the above
method, the protective film 8 can be formed by using a
focused ion beam (FIB).

To form the protective film 8 by the FIB, a Ga ion
10 beam is irradiated at positions on the alignment marks 12
while spraying an organic gas on a surface of the
membrane 2. Since the gas is decomposed by the energy of
the ion beam and a carbon film is deposited, ~~so that the~~
protective film 8 is formed partially. The carbon film
15 has sufficient resistance to washing performed after
removing the resist 3. Accordingly, when the carbon film
is formed to be a the thickness of transmitting an
exposure beam for alignment, it can be used as the
protective film 8.

20 When the protective film 8 is formed as shown in
FIG. 10A and FIG. 10B, conventionally--known mask side
alignment marks 7, as shown in FIG. 9, can be formed in
accordance with need. When the margin for matching is
large, it is not necessary to provide the mask side
25 alignment marks as shown in FIG. 9. When the mask side
alignment marks are not provided, alignment of the mask

blanks and the alignment substrate 11 is performed based
on the positions of the beams 4.

FIG. 11 shows a sectional view at the time of
performing alignment of the mask blanks having the
5 protective film 8 and the alignment substrate 11. When
the protective film 8 is formed, a high acceleration
electron beam used for mask exposure can be used for
alignment. As shown in FIG. 11, the high acceleration
electron beam 16B for alignment transmits through the
10 membrane 2 and the resist 3 thereon and is irradiated to
the alignment marks 12. An electron beam 17B reflected on
the alignment marks 12 is detected by an electron beam
detector 18B and positions of the alignment marks 12 are
measured.

15 ~~An~~-The alignment method shown in FIG. 11 is
particularly preferable to alignment at the time of mask
exposure for producing a stencil mask for LEEPL (low
energy electron proximity projection lithography), which
is one type of electron beam transfer ~~type~~ lithography.

20 In the LEEPL, an electron beam having an
accelerating voltage of, for example, 2 kV is used, and a
mask pattern is projected at the same magnification on
the wafer. Accordingly, it is necessary to form opening
portions in a finer pattern on the membrane than on the
25 mask to be used for reduced projection--type lithography.
When the membrane is thick, the aspect ratio of the

opening portions becomes high and fine processing becomes difficult, so that an extremely thin membrane is used for a mask for LEEPL.

Also, a high acceleration electron beam having an
5 accelerating voltage of, for example, 50 to 100 kV
transmits through a membrane having a thickness of
several hundreds nanometers or so, but a low acceleration
electron beam used in the LEEPL is blocked by a membrane
having a thickness of several hundreds nanometers or so
10 and selectively passes only through the opening portions,
so that a mask pattern is transferred.

On the other hand, since a high acceleration
electron beam is used for mask exposure for producing a
stencil mask for LEEPL, an electron beam for mask
15 exposure can be also used for alignment by transmitting
through the membrane and reflecting by the alignment
marks on the alignment substrate.

As shown in FIG. 8 and FIG. 11, the alignment
substrate, wherein positions of the alignment marks 12
20 are measured outside the mask exposure apparatus in
advance, and the mask blanks are set in the mask exposure
apparatus, and the alignment explained above is performed.
After that, a pattern is transferred to the resist by
mask exposure.

25 | When the relative positions of the mask blanks and
the alignment substrate shifts during ~~the~~ mask exposure,

positional accuracy of the mask exposure declines, so
that the aligned mask blanks and the alignment substrate
are fixed by using, for example, a pressing clamp and an
electrostatic chuck.

5 Furthermore, before transferring the mask blanks
and the alignment substrate to the mask exposure
apparatus, it is preferable that a stage of the mask
blanks and the alignment substrate at the time of
measuring positions of alignment marks with high accuracy
10 and a stage of the mask blanks and the alignment
substrate in the mask exposure apparatus have the same
mechanism. For example, when the mask blanks and the
alignment substrate are fixed by the pressing clamp, a
the holding mechanism of the pressing clamp is preferably
15 the same in the coordinates measuring device and the mask
exposure apparatus.

 In the alignment method of the present embodiment,
alignment is performed by using the alignment marks
arranged immediately under the membrane, so that a
20 generally used variety of alignment detection systems can
be applied in the same way as in the case where the
alignment marks are formed on the membrane. Also, as far
as it is not blocked by the membrane and the resist as
the upper layer, any light or charged particle beam may
25 be used for alignment, but the exposure beam for
alignment is not limited to this, and it may be a charged

particle beam, an extremely-short ultraviolet ray, an X-ray, an ultraviolet ray, radiation and/or visible light.

To perform alignment with high accuracy by a conventional alignment method, it ~~was~~is necessary that
5 alignment marks for mask exposure ~~were~~are provided to the respective mask blanks, but according to the alignment method of the present embodiment, alignment marks are provided to the alignment substrate placed under the mask blanks by being superimposed. Therefore,
10 it is not always necessary to form the alignment marks on the respective mask blanks. Due to this, the number of production steps and the production cost of a mask can be reduced.

Also, when performing alignment by providing
15 alignment marks on the respective mask blanks, there are some cases where the positions of the alignment marks are slightly different between the mask blanks due to an effect of an ~~the~~alignment mark formation process. Accordingly, it causes a deviation of alignment between
20 wirings of multilayer wiring of a semiconductor device or with a pattern (complementary divided pattern) formed on a complementary mask.

On the other hand, according to the alignment method of the present embodiment, since a common
25 alignment substrate is used for alignment of mask blanks on which different mask patterns are drawn, the positions

of the alignment marks do not vary and alignment accuracy between masks can be improved.

Embodiments of the alignment method, alignment substrate, production method of an alignment substrate, exposure method, exposure apparatus and production method of a mask are not limited to the above explanation. For example, a laser beam and electron beam are used for alignment in the above embodiments, but an X-ray or a white light having a broad wavelength band, etc., such as a charged particle beam, extremely-short ultraviolet ray, X-ray, ultraviolet ray, radiation and/or visible light, can be used for alignment.

Other than the above, a variety of modifications can be made within the scope of the present invention.

According to the alignment method of the present invention, alignment with high accuracy can be performed without providing alignment marks on a mask, and it is possible to prevent a decline of throughput of exposure and a decline of latent image contrast due to alignment.

According to the alignment substrate of the present invention, it is possible to improve superimposing accuracy or combining accuracy of patterns between masks formed with different mask patterns. According to the production method of the alignment substrate of the present invention, an alignment substrate capable of detecting alignment marks at high contrast can be

produced.

According to the exposure method and exposure apparatus of the present invention, it is possible to perform alignment with high accuracy when drawing a mask pattern even if alignment marks are not provided on the mask, and it is possible to prevent a decline of throughput of exposure and a decline of latent image contrast due to alignment.

According to the production method of a mask of the present invention, a lithography mask having a high positional accuracy of a mask pattern can be produced.

Industrial Applicability

The present invention can be applied to an alignment method for performing alignment in an exposure step, such as electron beam exposure, used in producing a semiconductor device, etc., an alignment substrate and the production method thereof, an exposure method used for producing a semiconductor device, etc., an exposure device, and a production method of a mask.

ABSTRACT

An alignment method capable of performing alignment
5 without providing alignment marks on a mask and
preventing a decline of exposure throughput and latent
image contrast, an alignment substrate and the production
method thereof, an exposure method, an exposure apparatus
and a production method of a mask are provided. An
10 alignment method including a step of transmitting a light
or a charged particle beam from a first surface side of a
thin film to a second surface side, reflecting the light
or charged particle beam on a plurality of alignment
marks arranged on the second surface side of the thin
15 film but outside the thin film, detecting the reflected
light or charged particle beam on the first surface side,
and detecting positions of the alignment marks, and a
step of obtaining position coordinates on the thin film;
an alignment substrate used for the alignment method and
20 a production method thereof, an exposure method for
performing the alignment, an exposure apparatus and a
production method of a mask are provided.